**PRODUCTION COMPOUND** 

# **BESTOLIFE 2000®**



5 Gallon Plastic Pail

#### **PRODUCT CHARACTERISTICS**

Color: Black-Copper Penetration: 310-330 (ASTM D 217) Weight/Gallon: 10.4 pounds/gallon Dropping Point: 350°F/177°C (typ) Flash Point: 385°F/196°C (min) Brushable To: 10°F/-12°C Friction Factor: 0.90 (relative API Modified)\* Contains: Inert non-metallic solids <4% copper

## PACKAGING

PRODUCT NUMBER	CONTAINER SIZE	CONTAINER WEIGHT
615009	1 gallon	9 pounds plastic
615018	2 gallon	18 pounds plastic
615030	3 1/2 gallon	30 pounds plastic
615045	5 gallon	45 pounds plastic

PREMIUM COMPOUNDS

## DESCRIPTION

BESTOLIFE 2000<sup>®</sup> is a lead-free, zinc-free thread compound for casing, tubing, and line pipe. It conforms to ISO 13678 and API RP 5A3 and is stable in high-pressure and hightemperature conditions. An excellent running compound, 2000<sup>®</sup> also provides superior protection for long-term storage.

## APPLICATIONS

Premium lead-free API alternative for casing, tubing, and line pipe; contains no lead or zinc.

## **TECHNICAL DATA**

BESTOLIFE 2000<sup>®</sup> will meet or exceed the listed performance objectives in ISO 13678 and API RP 5A3. The major solid components are a proprietary blend of nonmetallic materials that are inert to chemical attack, such as occurs in sour gas environments and with CO2 injection, and stable to temperatures in excess of 500° F.

BESTOLIFE 2000<sup>®</sup> also addresses one of the major concerns in pipe yards and threading operations today: rejects due to pitting and corrosion. In a 700-hour salt fog spray test, 2000<sup>®</sup> demonstrated corrosion protection that exceeds the performance of the leading storage compound in the industry.

## NOTES

A material safety data sheet is available from the manufacturer. Do not use on oxygen lines or in oxygen enriched atmospheres.

\*API RP 7A1: "Recommended Practice for Testing of Thread Compound for Rotary-Shouldered Connections" NOTE: Due to operation and equipment variables, this value may require adjustment based on field experience.



2777 N. Stemmons Fwy, Suite 1800 • Dallas, TX 75207 • (855) 243-9164

BESTOLIFE.COM