

DRILLING COMPOUND

COPPER SUPREME SPECIAL BLEND® PLUS



5 Gallon Plastic Pail

PRODUCT CHARACTERISTICS

Color: **Dark Copper**

Penetration: **310-330 (ASTM D 217)**

Weight/Gallon: **10.2 pounds/gallon**

Dropping Point: **500°F/260°C (typ)**

Flash Point: **385°F/196°C (min)**

Brushable To: **15°F/-9°C**

Friction Factor: **1.1 (per API RP 7A1)***

ASTM B117 Salt Spray Test: **2500 hours (min)**

Contains: **Copper flake, synthetic and amorphous graphite, and other non-metallic additives**

PACKAGING

PRODUCT NUMBER	CONTAINER SIZE	CONTAINER WEIGHT
635011	1 gallon	10 pounds plastic
635017	3 1/2 gallon	30 pounds plastic
635081	5 gallon	50 pounds plastic

*API RP 7A1: "Recommended Practice for Testing of Thread Compound for Rotary-Shouldered Connections" NOTE: Due to operation and equipment variables, this value may require adjustment based on field experience.

DESCRIPTION

BESTOLIFE Copper Supreme Special Blend® Plus (CSSB PLUS) adds a proprietary corrosion inhibitor to the original CSSB formula, providing excellent storage protection in addition to its superior running capabilities. CSSB PLUS guards against corrosion, resists washout, and will not harden or bleed excessively in storage.

APPLICATIONS

High temperature compound for drill collars and drill pipe with storage protection. Recommended for all drilling applications (rotary-shouldered connections), including high temperature environments. It is also effective for use on slides, jacking systems, cantilever type rigs and assemblies.

TECHNICAL DATA

CSSB PLUS contains copper flake combined with a proprietary blend of amorphous and synthetic graphite, oxidation, corrosion, and H₂S inhibitors, in a high temperature base grease.

NOTES

API and IADC tables for drill collars and drill pipe are minimum torque values. BESTOLIFE recommends an additional 10-15% torque beyond the minimum torque specified by these tables be applied, to ensure maximum performance and protection when using BESTOLIFE copper compounds.

A material safety data sheet is available from the manufacturer. Do not use on oxygen lines or in oxygen enriched atmosphere.



BESTOLIFE
PREMIUM COMPOUNDS

2777 N. Stemmons Fwy, Suite 1800 • Dallas, TX 75207 • (855) 243-9164

BESTOLIFE.COM